


COMPOSITION:




Compressed sheets for gasket made of mineral fibre, aramide and dispersed inorganic loads mixed in a matrix of type NBR rubber. The material is a sheet for gaskets for a wide range of applications. Its high compressibility, chemical resistance and good permeability make the BELPA CSA-48 suitable for most common uses, (water, air, oils, solvents, etc). It is also available with steel wire reinforcement and anti-stick coating. REF. BELPA CSA-48 M.

TECHNICAL DATA

Standard sizes (mm). Other upon request	1500 X 1500
Standard thickness (mm). Other upon request	0.5; 0.8; 1.0; 1.5; 2.0; 3.0
Density (+/-10%)	1.7 g/cm ³
Compressibility ASTM F-36 A	7% - 15%
Recovery ASTM F-36 A	>50%
Transverse tensile strength ASTM F-152	8 MPa
Gas permeability DIN 3535/6	< 1 cm ³ /min
THICKNESS INCREASE ASTM F-146	
ASTM oil N°3 5h 150°C	<10%
ASTM fuel B 5h 20°C	<10%
* Typical properties for 2 mm thickness.	

PRESSURE - TEMPERATURE DIAGRAM



P-T OPERATING GUIDELINES:

- 1- Usually satisfactory to use without reference to Montero. Technical examination is normally unnecessary.
- 2- Must refer to Montero for advice. A technical examination is recommended.
- 3- Area not recommended.

The P-T diagram helps the user or designer who often knows the operating temperature and pressure to carry out an initial selection of a suitable material. The P-T diagram cannot guarantee the suitability of a material for an application.

Good performance and long service life of gaskets depend in large measure on fitting and operation conditions, over which the manufacturer has no control. The data given on this technical sheet should not be used as application limits, but as guidance for an appropriate choice. We can offer guarantees only for the quality of our products.